

HLMP-LG70/71, HLMP-LB71**HLMP-LM71**

4 mm Oval Precision Optical Performance LED



Reliability Datasheet

Description

The following cumulative test results have been obtained from testing performed at Avago Technologies in accordance with the latest revisions of MIL-STD-883 and JIS C 7021.

Avago Technologies tests parts at the absolute maximum rated conditions recommended for the device. The actual performance you obtain from Avago technologies' parts depends on the electrical and environmental characteristics of your application but will probably be better than the performance outlined in below tables.

Failure Rate Prediction

The failure rate of semiconductor devices is determined by the junction temperature of the device. The relationship between ambient temperature and actual junction temperature is given by the following:

$$T_J (\text{°C}) = T_A (\text{°C}) + \theta_{JA} P_{AVG}$$

where

T_A = ambient temperature in °C

θ_{JA} = thermal resistance of junction-to-ambient in °C/watt

P_{AVG} = average power dissipated in watts

The estimated MTBF and failure rate at temperatures lower than the actual stress temperature can be determined by using an Arrhenius model for temperature acceleration. Results of such calculations are shown in the table on the following page using activation energy of 0.43 eV (reference MIL-HDBK-217).

**Table 1. Life Tests
Demonstrated Performance**

Die Type	Stress Test Conditions	Total Device Hrs.	Units Tested	Units Failed	Point Typical Performance	
					Failure Rate	MTBF (%/1 K Hours)
AllInGap	$T_A = 55^\circ\text{C}$ $I_F = 47 \text{ mA}$	168,000	168	0	189200	0.53
InGaN	$T_A = 55^\circ\text{C}$ $I_F = 23 \text{ mA}$	672,000	672	0	747,100	0.13

Table 2. Reliability Predictions ($I_F = 20$ mA)

Die Type: AlInGaP

Ambient Temperature (°C)	Junction Temperature (°C)	Point Typical Performance in Time [1]		Performance in Time [2]	
		MTTF [1] (60% Confidence)	Failure Rate (%/1 K Hours)	MTTF [2] (90% Confidence)	Failure Rate
100	130	178300	0.56	71000	1.41
95	130	179500	0.56	71400	1.40
90	129	180600	0.55	71900	1.39
85	129	181800	0.55	72400	1.38
80	129	183000	0.55	72900	1.37
75	129	184200	0.54	73300	1.36
70	129	185500	0.54	73800	1.36
65	128	186700	0.54	74300	1.35
60	128	187900	0.53	74800	1.34
55	128	189200	0.53	75300	1.33
50	128	190400	0.53	75800	1.32
45	124	216200	0.46	86100	1.16
40	119	253800	0.39	101000	0.99
35	114	299300	0.33	119100	0.84
30	109	354400	0.28	141100	0.71
25	104	421500	0.24	167800	0.60
20	99	503700	0.20	200500	0.50

Table 3. Reliability Predictions ($I_F = 20$ mA)**Die Type: InGaN**

Ambient Temperature (°C)	Junction Temperature (°C)	Point Typical Performance in Time [1] (60% Confidence)		Performance in Time [2] (90% Confidence)	
		MTTF [1]	Failure Rate (%/1 K Hours)	MTTF [2]	Failure Rate (%/1 K Hours)
85	108	742500	0.13	295600	0.34
80	108	743300	0.13	295900	0.34
75	108	744100	0.13	296200	0.34
70	108	744800	0.13	296500	0.34
65	108	745600	0.13	296800	0.34
60	108	746300	0.13	297100	0.34
55	108	747100	0.13	297400	0.34
50	108	747900	0.13	297700	0.34
45	108	748600	0.13	298000	0.34
40	108	749400	0.13	298300	0.34
35	105	831800	0.12	331100	0.30
30	100	992700	0.10	395200	0.25
25	95	1190500	0.08	473900	0.21
20	90	1434900	0.07	571200	0.18
15	85	1738500	0.06	692000	0.14
10	80	2117700	0.05	843000	0.12
5	75	2594400	0.04	1032700	0.10

Notes:

1. The point typical MTBF (which represents 60% confidence level) is the total device hours divided by the number of failures. In the case of zero failures, one failure is assumed for this calculation.
2. The 90% Confidence MTBF represents the minimum level of reliability performance which is expected from 90% of all samples. This confidence interval is based on the statistics of the distribution of failures. The assumed distribution of failures is exponential. This particular distribution is commonly used in describing useful life failures. Refer to MIL-STD-690B for details on this methodology.
3. A failure is any LED which is open, shorted, or fails to emit light
4. Calculated from data generated at 55°C biased at 50 mA.

Failure Rate Calculation (Example AllInGaP Die Type Package):

Assume a device operating 8 hours/day, 5 days/week. The utilization factor, given 168 hours/week is:

$$(8 \text{ hours/day}) \times (5 \text{ days/week}) / (168 \text{ hours/week}) = 0.24$$

The point failure rate per year (8760 hours) at 25°C ambient temperature is: (60% confidence level) :

$$(0.24\%/\text{1 K hours}) \times (0.24) \times (8760 \text{ hours/year}) = 0.5\% \text{ per year}$$

Similarly, 90% confidence level failure rate per year at 25°C:

$$(0.6\%/\text{1 K hours}) \times (0.24) \times (8760 \text{ hours/year}) = 1.26\% \text{ per year}$$

Table 4. Environmental/ Operating Tests

Test Name	MIL-STD/JEDEC Reference	Test Conditions	Units Tested	Units Failed
Temperature Cycle	JESDA104	-40°C/100°C, 30 min dwell, 5 min transfer, 100 cycles	3744	0
Temperature Humidity Operating Life	JESD 22-A101	T _A = 85° C, RH = 85%RH, 1000 hrs AlInGaP 28 mA, InGaN 10 mA	84	0
High Temperature Operating Life	JESDA103	T _A = 55° C, 1000 hrs AlInGaP 47 mA, InGaN 23 mA	168	0
Low Temperature Operating Life	JESD 22-A108	T _A = -40° C, 1000 hrs AlInGaP 50 mA, InGaN 30 mA	84	0
Temperature Humidity Storage Life	Avago Requirement	T _A = 85° C, RH = 85%RH, 1000 hrs	672	0
Pulse Test	Avago Requirement	T _A = 85° C, If = 100 mA, Peak, Freq: 1 Khz, AlInGaP DF: 30%; InGaN DF: 10%	84	0
Resistance to Solder heat	JESDB106	260+/-5° C, 10+/-2 second, 2x	30	0

For product information and a complete list of distributors, please go to our web site: www.avagotech.com

Avago, Avago Technologies, and the A logo are trademarks of Avago Technologies in the United States and other countries.
 Data subject to change. Copyright © 2005-2012 Avago Technologies. All rights reserved.
 AV02-3406EN - March 30, 2012





**Стандарт
Электрон
Связь**

Мы молодая и активно развивающаяся компания в области поставок электронных компонентов. Мы поставляем электронные компоненты отечественного и импортного производства напрямую от производителей и с крупнейших складов мира.

Благодаря сотрудничеству с мировыми поставщиками мы осуществляем комплексные и плановые поставки широчайшего спектра электронных компонентов.

Собственная эффективная логистика и склад в обеспечивает надежную поставку продукции в точно указанные сроки по всей России.

Мы осуществляем техническую поддержку нашим клиентам и предпродажную проверку качества продукции. На все поставляемые продукты мы предоставляем гарантию .

Осуществляем поставки продукции под контролем ВП МО РФ на предприятия военно-промышленного комплекса России , а также работаем в рамках 275 ФЗ с открытием отдельных счетов в уполномоченном банке. Система менеджмента качества компании соответствует требованиям ГОСТ ISO 9001.

Минимальные сроки поставки, гибкие цены, неограниченный ассортимент и индивидуальный подход к клиентам являются основой для выстраивания долгосрочного и эффективного сотрудничества с предприятиями радиоэлектронной промышленности, предприятиями ВПК и научно-исследовательскими институтами России.

С нами вы становитесь еще успешнее!

Наши контакты:

Телефон: +7 812 627 14 35

Электронная почта: sales@st-electron.ru

Адрес: 198099, Санкт-Петербург,
Промышленная ул, дом № 19, литер Н,
помещение 100-Н Офис 331