RTV Silicones

RTV Number... GO

ALL MG PRODUCTS

Jump to Product Number

Product Number... GO

- Accessories
- Adhesives
- Brushes
- Cleaners / Degreasers
- Contact Cleaners
- Desoldering Braid
- Dusters & Circuit Coolers
- EMI / RFI Shielding
- Epoxies
- Flux and Flux Remover
- Glass & Screen Cleaners
- Isopropyl Alcohol
- Lead Free Solder
- Lubricants
- Potting & Encapsulating
- Protective Coatings
- Pens
- Prototyping Materials
- RTV Silicones
- Soldering/desoldering
- Specialized Cleaners
- Swabs
- Thermal Management
- Thermally Conductive Adhesives
- Wipes

RTV Silicones by MOMENTIVE performance materials

1-Part Adhesive Sealant RTV167

RoHS COMPLIANT

BUY NOW

Primary Characteristics

- Light Gray Paste
- **High strength electronics**
- Non-corrosive
- Alkoxy neutral cure
- MIL-A-46146, group 1, type 1
- UL HB recognition
- UL File No. E36952

Excellent in areas that require an extra strength sealing and bonding. Non-corrosive to electronic metals, including copper and brass. Can be applied to vertical or overhead surfaces. Retains elastomeric properties for long periods at temperatures from -60°C to 205°C (75°F to 400°F) and for short periods up to 250°C (500°F). Excellent electrical insulating properties. This product meets Military spec. MIL-A-46146 and is UL HB recognized.

Available Sizes

Catalog Number	Sizes Available	Description	Case Qty
RTV167-85ML	85 mL (2.8 oz)	Tube	12
RTV167-300ML SPECIAL ORDER	300mL (10 oz)	Cartridge	24

Specifications

Use	Adhesive Sealant
Special Feature	High tensile strength
Standards	MIL-A-46146, group 1, type 1
	UL File no. E-36952
Cross Reference	RTV167
Uncured Properties	
Consistency	Paste
Color	Grey
Specific Gravity	1.12
Tack Free Time	4 hours
Cure through time	48 hours
Useful Temp. Range	-60°C to 205°C (-75°F to 400°F)
Cured Properties - MECHANICAL	
Hardness	37 (Shore A)
Tensile Strength	5.49 MPa (800 psi)
Elongation	600%
Peel Strength	10 kg/cm
	80 lb/in
Cured Properties - ELECTRICAL	
Volume Resistivity	3 x 10^{15} ohm · cm
Dielectric Strength	19.7 kV/mm
	500 V/mil
Dielectric Constant	2.8 @ 60 Hz
Cured Properties - THERMAL	

Technical Support for RTV Silicones

☎1-800-255-8886

M.G. Chemicals Disclaimer for RTV Silicones >

Locate Distributor >

Quick Links

- MSDS
- Specifications
- Available Sizes

Related products:

- RTV160 White
- RTV162 White
- TSE397C Clear
- TSE399C Clear

Resources

- Selection Guide
- One Part Chart
- Two Part Chart

Find by Application

- General Purpose
- Aerospace
- Marine
- High Performance Assembly
- Electronics
- Thermal Conductivity
- High Temperature
- Low Temperature

Google

Google Search MG

Thermal Conductivity	0.21 W/m · °K
Brittle Point	-60°C (-75°F)
Thermal Expansion	27 x 10^{-5} $(°C)^{-1}$
Other	
Viscosity (@ 25°C)	180 g/min

Return to top ^

© 2000 - 2007 MG Chemicals. All rights reserved. Site Map Terms & Conditions Contact Us

web site design by offbeat studio

Стандарт Электрон Связь

Мы молодая и активно развивающаяся компания в области поставок электронных компонентов. Мы поставляем электронные компоненты отечественного и импортного производства напрямую от производителей и с крупнейших складов мира.

Благодаря сотрудничеству с мировыми поставщиками мы осуществляем комплексные и плановые поставки широчайшего спектра электронных компонентов.

Собственная эффективная логистика и склад в обеспечивает надежную поставку продукции в точно указанные сроки по всей России.

Мы осуществляем техническую поддержку нашим клиентам и предпродажную проверку качества продукции. На все поставляемые продукты мы предоставляем гарантию .

Осуществляем поставки продукции под контролем ВП МО РФ на предприятия военно-промышленного комплекса России , а также работаем в рамках 275 ФЗ с открытием отдельных счетов в уполномоченном банке. Система менеджмента качества компании соответствует требованиям ГОСТ ISO 9001.

Минимальные сроки поставки, гибкие цены, неограниченный ассортимент и индивидуальный подход к клиентам являются основой для выстраивания долгосрочного и эффективного сотрудничества с предприятиями радиоэлектронной промышленности, предприятиями ВПК и научно-исследовательскими институтами России.

С нами вы становитесь еще успешнее!

Наши контакты:

Телефон: +7 812 627 14 35

Электронная почта: sales@st-electron.ru

Адрес: 198099, Санкт-Петербург, Промышленная ул, дом № 19, литера Н, помещение 100-Н Офис 331