

SPECIFICATION CONTROL DRAWING

55/0312

TITLE	WIRE, RADIATION-CROSSLINKED MODIFIED ETFE INSULATED, ULTRA LIGHTWEIGHT, OUTER SPACE, 600 VOLT	Date	1-30-06	Revision	J
-------	--	------	---------	----------	---

This specification sheet forms a part of the latest issue of Raychem Specification 55/.

CONDUCTOR - SILVER-COATED COPPER

INSULATION - LOW OUTGASSING
RADIATION-CROSSLINKED,
MODIFIED ETFE




TABLE I. CONSTRUCTION DETAILS

PART NUMBER 1/	WIRE SIZE (AWG)	CONDUCTOR STRANDING (number x AWG)	DIAMETER OF STRANDED CONDUCTOR (in.)		FINISHED WIRE		
			MINIMUM	MAXIMUM	MAXIMUM RESISTANCE AT 20°C (ohms/1000 ft.)	DIAMETER (in.)	MAXIMUM WEIGHT (lbs/1000 ft.)
55/0312-28-*	28	7 x 36	.0140	.0150	63.8	.0225 ± .0015	.81
55/0312-26-*	26	19 x 38	.0175	.0191	38.4	.0274 ± .0017	1.22
55/0312-24-*	24	19 x 36	.0225	.0241	24.3	.0322 ± .0017	1.80
55/0312-22-*	22	19 x 34	.0285	.0301	15.1	.0390 ± .0017	2.70
55/0312-20-*	20	19 x 32	.0365	.0385	9.19	.0495 ± .0017	4.27
55/0312-18-*	18	19 x 30	.0452	.0476	5.79	.0590 ± .0017	6.56
55/0312-16-*	16	19 x 29	.0514	.0538	4.52	.0665 ± .0019	8.33
55/0312-14-*	14	19 x 27	.0644	.0674	2.88	.0810 ± .0021	12.81
55/0312-12-*	12	37 x 28	.0825	.0865	1.90	.1000 ± .0026	19.71
55/0312-10-*	10	37 x 26	.1050	.1090	1.19	.1260 ± .0040	31.70

TABLE II. PERFORMANCE DETAILS

BEND TESTING		
PART NUMBER 1/	MANDREL DIAMETER (inch) (± 3%)	WEIGHT (lb) (± 3%)
	CROSSLINK VERIFICATION	CROSSLINK VERIFICATION
55/0312-28-*	.250	.063
55/0312-26-*	.375	.063
55/0312-24-*	.375	.125
55/0312-22-*	.500	.188
55/0312-20-*	.500	.250
55/0312-18-*	.500	.250
55/0312-16-*	.750	.375
55/0312-14-*	1.00	.500
55/0312-12-*	1.50	.750
55/0312-10-*	2.00	.750

WIRE RATINGS AND ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 200°C

Maximum continuous conductor temperature

VOLTAGE RATING: 600 volts (rms) at sea level

CROSSLINK VERIFICATION: 300 ± 3°C for 1 hour

COLOR: White preferred

CONCENTRICITY: 80% (minimum)

IDENTIFICATION AND COLOR STRIPING DURABILITY:

125 cycles (250 strokes) (minimum), 500 g weight

INSULATION ELONGATION: 50% (minimum)

INSULATION FLAWS:

Spark Test, 1.5 kV (rms), (28 - 24 AWG)

3.0 kV (rms), (22 AWG & larger)

Impulse Dielectric Test, 6.0 kV (peak)

INSULATION THICKNESS: .004 in. (nominal)

RADIATION RESISTANCE: 500 megarads

SHRINKAGE: 230 ± 3°C for 1 hour, 0.125 in. (maximum) in 12 in.

VACUUM STABILITY:

Total Mass Loss (TML), 1.0% (maximum)

Volatle Condensable Material (VCM), 0.1% (maximum)

VOLTAGE WITHSTAND TEST (Post Environmental):

1500 volts (rms), 60 Hz, 5 minutes

PART NUMBER:

The "*" in the part numbers above shall be replaced
by color code designators.

1/ Example: AWG 20, white: 55/0312-20-9

Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice.

Tyco Electronics also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer.

1/ COLORS AND COLOR CODE DESIGNATORS SHALL BE IN ACCORDANCE WITH MIL-STD-681. OTHER CODES
AND SUFFIXES MAY BE ADDED TO THE PART NUMBER, AS NECESSARY, TO CAPTURE ANY ADDITIONAL
REQUIREMENTS IMPOSED BY THE PURCHASE ORDER.

tyco
Electronics

Raychem Wire & Cable
501 Oakside Avenue
Redwood City, CA 94063-3800
Phone: 1-800-227-8816
Fax: 1-650-361-6297



**Стандарт
Электрон
Связь**

Мы молодая и активно развивающаяся компания в области поставок электронных компонентов. Мы поставляем электронные компоненты отечественного и импортного производства напрямую от производителей и с крупнейших складов мира.

Благодаря сотрудничеству с мировыми поставщиками мы осуществляем комплексные и плановые поставки широчайшего спектра электронных компонентов.

Собственная эффективная логистика и склад в обеспечивает надежную поставку продукции в точно указанные сроки по всей России.

Мы осуществляем техническую поддержку нашим клиентам и предпродажную проверку качества продукции. На все поставляемые продукты мы предоставляем гарантию .

Осуществляем поставки продукции под контролем ВП МО РФ на предприятия военно-промышленного комплекса России , а также работаем в рамках 275 ФЗ с открытием отдельных счетов в уполномоченном банке. Система менеджмента качества компании соответствует требованиям ГОСТ ISO 9001.

Минимальные сроки поставки, гибкие цены, неограниченный ассортимент и индивидуальный подход к клиентам являются основой для выстраивания долгосрочного и эффективного сотрудничества с предприятиями радиоэлектронной промышленности, предприятиями ВПК и научно-исследовательскими институтами России.

С нами вы становитесь еще успешнее!

Наши контакты:

Телефон: +7 812 627 14 35

Электронная почта: sales@st-electron.ru

Адрес: 198099, Санкт-Петербург,
Промышленная ул, дом № 19, литера Н,
помещение 100-Н Офис 331