

Conductive Film 1700 Series

Conductive Film 1700 is opaque, volume-conductive, carbon-impregnated polyolefin, and is commonly used for material handling, shipping and storage in the electronic or chemical industries.



RoHS 2, REACH, and Conflict Minerals Statement

None of the RoHS 2 restricted materials or REACH substances of very high concern as of 2015/06/15, or Conflict Minerals are intentionally added in manufacturing this product. Ref: European Union Directive 2011/65/EU and Regulation (EC) No. 1907/2006/CE. See [SCS Warranty, Limitation of Liability and Remedies](#)

Film is free of amines, silicones and heavy metals.

This product is intended for commercial use only. This product is not on the Qualified Product Listing under the Defense Standardization Program.

Unless otherwise specified tolerance $\pm 10\%$.

Conductive Film, Short Rolls 1704, 1706, 1708

Type	Conductive
Film Thickness for 1704	4.0 mil (102 microns)
Film Thickness for 1706	6.0 mil (152.4 microns)
Film Thickness for 1708	8.0 mil (203.2 microns)

Standard Sizes	
Roll Length 150 ft. (45.7 m)	36 in. (91.4 cm) (Items: 1704, 1706, 1708) 45 in. (114.3 cm) (Item: 1706) 54 in. (137.2 cm) (Items: 1704, 1708) 72 in. (182.9 cm) (Items: 1704, 1706, 1708)

Conductive Film, Long Rolls, 1764

Type	Conductive
Film Thickness	4.0 mil (102 microns)

Standard Size	
Roll Length 1,500 ft. (457.2 m)	36 in. (91.4 cm)

Specifications

Property	Test Method	Typical Value
Thickness	ASTM D2103	4 mil (102 microns)
Strength		
Breaking Factor	ASTM D882	8 lbs./in.
Puncture	Fed Std 101	7 lbs.
Heat Seal Parameters		
Temperature		250°F
Time		3.0-5.0 sec.
Pressure		20-60 PSI
Vicat Softening Temperature	ASTM D1525	83°C
Electrical Properties		
Volume Resistivity	ASTM D991	<500 ohm-cm
Static Decay	EIA-541	<2 sec.
Chemical Susceptibility		
Dilute Acids and Alkalies	ASTM D543	Resistant
Alcohols (Isopropanol)		Resistant
Hydrocarbons (Acetone)		Moderate attack
Ketones (Acetone)		Slight attack
Gasoline		Moderate attack
Aromatic Hydrocarbons (Toluene)		Severe attack

Specifications and procedures subject to change without notice.



Made in the United States of America



SCS

CONDUCTIVE FILM 1700 SERIES

926 JR Industrial Drive, Sanford, NC 27332
WEB SITE: StaticControl.com
PHONE (919) 718-0000

DRAWING NUMBER
1700 SERIES

DATE
February 2016



Стандарт Электрон Связь

Мы молодая и активно развивающаяся компания в области поставок электронных компонентов. Мы поставляем электронные компоненты отечественного и импортного производства напрямую от производителей и с крупнейших складов мира.

Благодаря сотрудничеству с мировыми поставщиками мы осуществляем комплексные и плановые поставки широчайшего спектра электронных компонентов.

Собственная эффективная логистика и склад в обеспечивает надежную поставку продукции в точно указанные сроки по всей России.

Мы осуществляем техническую поддержку нашим клиентам и предпродажную проверку качества продукции. На все поставляемые продукты мы предоставляем гарантию .

Осуществляем поставки продукции под контролем ВП МО РФ на предприятия военно-промышленного комплекса России , а также работаем в рамках 275 ФЗ с открытием отдельных счетов в уполномоченном банке. Система менеджмента качества компании соответствует требованиям ГОСТ ISO 9001.

Минимальные сроки поставки, гибкие цены, неограниченный ассортимент и индивидуальный подход к клиентам являются основой для выстраивания долгосрочного и эффективного сотрудничества с предприятиями радиоэлектронной промышленности, предприятиями ВПК и научно-исследовательскими институтами России.

С нами вы становитесь еще успешнее!

Наши контакты:

Телефон: +7 812 627 14 35

Электронная почта: sales@st-electron.ru

Адрес: 198099, Санкт-Петербург,
Промышленная ул, дом № 19, литера Н,
помещение 100-Н Офис 331