
# X7R Dielectric

## General Specifications



X7R formulations are called “temperature stable” ceramics and fall into EIA Class II materials. X7R is the most popular of these intermediate dielectric constant materials. Its temperature variation of capacitance is within ±15% from -55°C to +125°C. This capacitance change is non-linear.

Capacitance for X7R varies under the influence of electrical operating conditions such as voltage and frequency.

X7R dielectric chip usage covers the broad spectrum of industrial applications where known changes in capacitance due to applied voltages are acceptable.


RoHS COMPLIANT

## PART NUMBER (see page 2 for complete part number explanation)


| 0805 | 5 | C | 103 | M | A | T | 2 | A |
|---|---|---|---|---|---|---|---|---|
| **Size** (L" x W") | **Voltage** 4V = 4, 6.3V = 6, 10V = Z, 16V = Y, 25V = 3, 50V = 5, 100V = 1, 200V = 2, 500V = 7 | **Dielectric** X7R = C | **Capacitance Code (In pF)** 2 Sig. Digits + Number of Zeros | **Capacitance Tolerance** J = ± 5%* K = ±10% M = ± 20% *≤1µF only, contact factory for additional values | **Failure Rate** A = Not Applicable | **Terminations** T = Plated Ni and Sn 7 = Gold Plated* Z = FLEXITERM®** *Optional termination **See FLEXITERM® X7R section | **Packaging** 2 = 7" Reel 4 = 13" Reel 7 = Bulk Cass. 9 = Bulk **Contact Factory For Multiples** | **Special Code** A = Std. Product |

NOTE: Contact factory for availability of Termination and Tolerance Options for Specific Part Numbers. Contact factory for non-specified capacitance values.


**X7R Dielectric**
**Typical Temperature Coefficient**





**Δ Capacitance vs. Frequency**





**Insulation Resistance vs Temperature**





**Variation of Impedance with Cap Value**
**Impedance vs. Frequency**
**1,000 pF vs. 10,000 pF - X7R**
**0805**




**Variation of Impedance with Chip Size**
**Impedance vs. Frequency**
**10,000 pF - X7R**





**Variation of Impedance with Chip Size**
**Impedance vs. Frequency**
**100,000 pF - X7R**



# X7R Dielectric

## Specifications and Test Methods

| Parameter/Test | | X7R Specification Limits | Measuring Conditions | |
|---|---|---|---|---|
| **Operating Temperature Range** | | -55ºC to +125ºC | Temperature Cycle Chamber | |
| **Capacitance** | | Within specified tolerance | Freq.: 1.0 kHz ± 10%<br>Voltage: 1.0Vrms ± .2V | |
| **Dissipation Factor** | | ≤ 2.5% for ≥ 50V DC rating<br>≤ 3.0% for 25V DC rating<br>≤ 3.5% for 25V and 16V DC rating<br>≤ 5.0% for ≤ 10V DC rating | | |
| **Insulation Resistance** | | 100,000MΩ or 1000MΩ - µF, whichever is less | Charge device with rated voltage for 120 ± 5 secs @ room temp/humidity | |
| **Dielectric Strength** | | No breakdown or visual defects | Charge device with 300% of rated voltage for 1-5 seconds, w/charge and discharge current limited to 50 mA (max)<br>Note: Charge device with 150% of rated voltage for 500V devices. | |
| **Resistance to Flexure Stresses** | Appearance | No defects | Deflection: 2mm<br>Test Time: 30 seconds<br> | |
| | Capacitance Variation | ≤ ±12% | | |
| | Dissipation Factor | Meets Initial Values (As Above) | | |
| | Insulation Resistance | ≥ Initial Value x 0.3 | | |
| **Solderability** | | ≥ 95% of each terminal should be covered with fresh solder | Dip device in eutectic solder at 230 ± 5ºC for 5.0 ± 0.5 seconds | |
| **Resistance to Solder Heat** | Appearance | No defects, <25% leaching of either end terminal | Dip device in eutectic solder at 260ºC for 60 seconds. Store at room temperature for 24 ± 2 hours before measuring electrical properties. | |
| | Capacitance Variation | ≤ ±7.5% | | |
| | Dissipation Factor | Meets Initial Values (As Above) | | |
| | Insulation Resistance | Meets Initial Values (As Above) | | |
| | Dielectric Strength | Meets Initial Values (As Above) | | |
| **Thermal Shock** | Appearance | No visual defects | Step 1: -55ºC ± 2º | 30 ± 3 minutes |
| | Capacitance Variation | ≤ ±7.5% | Step 2: Room Temp | ≤ 3 minutes |
| | Dissipation Factor | Meets Initial Values (As Above) | Step 3: +125ºC ± 2º | 30 ± 3 minutes |
| | Insulation Resistance | Meets Initial Values (As Above) | Step 4: Room Temp | ≤ 3 minutes |
| | Dielectric Strength | Meets Initial Values (As Above) | Repeat for 5 cycles and measure after 24 ± 2 hours at room temperature | |
| **Load Life** | Appearance | No visual defects | Charge device with 1.5 rated voltage (≤ 10V) in test chamber set at 125ºC ± 2ºC for 1000 hours (+48, -0)<br><br>Remove from test chamber and stabilize at room temperature for 24 ± 2 hours before measuring. | |
| | Capacitance Variation | ≤ ±12.5% | | |
| | Dissipation Factor | ≤ Initial Value x 2.0 (See Above) | | |
| | Insulation Resistance | ≥ Initial Value x 0.3 (See Above) | | |
| | Dielectric Strength | Meets Initial Values (As Above) | | |
| **Load Humidity** | Appearance | No visual defects | Store in a test chamber set at 85ºC ± 2ºC/ 85% ± 5% relative humidity for 1000 hours (+48, -0) with rated voltage applied.<br><br>Remove from chamber and stabilize at room temperature and humidity for 24 ± 2 hours before measuring. | |
| | Capacitance Variation | ≤ ±12.5% | | |
| | Dissipation Factor | ≤ Initial Value x 2.0 (See Above) | | |
| | Insulation Resistance | ≥ Initial Value x 0.3 (See Above) | | |
| | Dielectric Strength | Meets Initial Values (As Above) | | |

# X7R Dielectric

## Capacitance Range

### PREFERRED SIZES ARE SHADED

| SIZE | | 0101 | 0201 | | | 0402 | | | 0603 | | | | | | | 0805 | | | | | | | 1206 | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Soldering | | Reflow Only | Reflow Only | | | Reflow/Wave | | | Reflow/Wave | | | | | | | Reflow/Wave | | | | | | | Reflow/Wave | | | | | | | |
| Packaging | | Paper/Embossed | All Paper | | | All Paper | | | All Paper | | | | | | | Paper/Embossed | | | | | | | Paper/Embossed | | | | | | | |
| (L) Length | mm | 0.40 ± 0.02 | 0.60 ± 0.03 | | | 1.00 ± 0.10 | | | 1.60 ± 0.15 | | | | | | | 2.01 ± 0.20 | | | | | | | 3.20 ± 0.20 | | | | | | | |
| | (in.) | (0.016 ± 0.0008) | (0.024 ± 0.001) | | | (0.040 ± 0.004) | | | (0.063 ± 0.006) | | | | | | | (0.079 ± 0.008) | | | | | | | (0.126 ± 0.008) | | | | | | | |
| (W) Width | mm | 0.20 ± 0.02 | 0.30 ± 0.03 | | | 0.50 ± 0.10 | | | 0.81 ± 0.15 | | | | | | | 1.25 ± 0.20 | | | | | | | 1.60 ± 0.20 | | | | | | | |
| | (in.) | (0.008 ± 0.0008) | (0.011 ± 0.001) | | | (0.020 ± 0.004) | | | (0.032 ± 0.006) | | | | | | | (0.049 ± 0.008) | | | | | | | (0.063 ± 0.008) | | | | | | | |
| (t) Terminal | mm | 0.20 ± 0.02 | 0.15 ± 0.05 | | | 0.25 ± 0.15 | | | 0.35 ± 0.15 | | | | | | | 0.50 ± 0.25 | | | | | | | 0.50 ± 0.25 | | | | | | | |
| | (in.) | (0.008 ± 0.0008) | (0.006 ± 0.002) | | | (0.010 ± 0.006) | | | (0.014 ± 0.006) | | | | | | | (0.020 ± 0.010) | | | | | | | (0.020 ± 0.010) | | | | | | | |
| | WVDC | 10 | 10 | 16 | 25 | 16 | 25 | 50 | 6.3 | 10 | 16 | 25 | 50 | 100 | 200 | 6.3 | 10 | 16 | 25 | 50 | 100 | 200 | 6.3 | 10 | 16 | 25 | 50 | 100 | 200 | 500 |
| Cap | 100 | A | A | A | A | | | | | | | | | | | | | | | | | | | | | | | | | |
| (pF) | 150 | A | A | A | A | | | | | | | | | | | | | | | | | | | | | | | | | |
| | 220 | A | A | A | A | | | C | | | | | | | | | | | | | | | | | | | | | | |
| | 330 | A | A | A | A | | | C | | | | | G | G | G | | J | J | J | J | J | J | | | | | | | | K |
| | 470 | A | A | A | | | | C | | | | | G | G | G | | J | J | J | J | J | J | | | | | | | | K |
| | 680 | A | A | A | | | | C | | | | | G | G | G | | J | J | J | J | J | J | | | | | | | | K |
| | 1000 | A | A | A | | | | C | | | | | G | G | G | | J | J | J | J | J | J | | | | | | | | K |
| | 1500 | | A | | | | | C | | | | | G | G | | | J | J | J | J | J | J | | J | J | J | J | J | J | M |
| | 2200 | | A | | | | | C | | | | | G | G | | | J | J | J | J | J | J | | J | J | J | J | J | J | M |
| | 3300 | | A | | | | C | C | | | | | G | G | | | J | J | J | J | J | J | | J | J | J | J | J | J | M |
| | 4700 | | A | | | | C | C | | | | | G | G | | | J | J | J | J | J | J | | J | J | J | J | J | J | M |
| | 6800 | | A | | | C | C | | | | | | G | G | | | J | J | J | J | J | J | | J | J | J | J | J | J | P |
| Cap | 0.010 | | A | | | C | C | | | | | | G | G | | | J | J | J | J | J | J | | J | J | J | J | J | J | P |
| (µF | 0.015 | | | | | C | | | | | | G | G | | | | J | J | J | J | J | | J | J | J | J | M | | |
| | 0.022 | | | | | C | C | | | | | G | G | | | | J | J | J | J | J | N | | J | J | J | J | M | | |
| | 0.033 | | | | | C | C | | | | | G | G | | | | J | J | J | J | N | | | J | J | J | J | M | | |
| | 0.047 | | | | | C | C | | | | G | G | G | | | | J | J | J | J | N | | | J | J | J | J | M | | |
| | 0.068 | | | | | C | C | | | | G | G | G | | | | J | J | J | J | N | | | J | J | J | J | P | | |
| | 0.10 | | | | | C | C | | | G | G | G | G | | | | J | J | J | J | N | | | J | J | J | M | P | | |
| | 0.15 | | | | | | | | G | G | | | | | | | J | J | J | N | N | | | J | J | J | Q | | | |
| | 0.22 | | | | | | | | G | G | | J* | | | | | J | J | N | N | N | | | J | J | J | Q | | | |
| | 0.33 | | | | | | | | | | | | | | | | N | N | N | N | N | | | J | J | M | P | Q | | |
| | 0.47 | | | | | | | | | | | J* | | | | | N | N | N | N | N | | | M | M | M | P | Q | | |
| | 0.68 | | | | | | | | | | | | | | | | N | N | N | | | | | M | M | Q | Q | Q | | |
| | 1.0 | | | | | | | | | J* | J* | | | | | | N | N | N | N | | | | M | M | Q | Q | Q | | |
| | 1.5 | | | | | | | | | | | | | | | | | | | | | | | P | Q | Q | | | | |
| | 2.2 | | | | | | | | J* | | | | | | | | | | P* | | | | | Q | Q | Q | | Q* | | |
| | 3.3 | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | 4.7 | | | | | | | | | | | | | | | | P* | P* | | | | | | Q* | Q* | Q* | Q* | | | |
| | 10 | | | | | | | | | | | | | | | P* | P* | | | | | | | Q* | Q* | Q* | | | | |
| | 22 | | | | | | | | | | | | | | | | | | | | | | Q* | Q* | | | | | | |
| | 47 | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | 100 | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | WVDC | 10 | 10 | 16 | 25 | 16 | 25 | 50 | 6.3 | 10 | 16 | 25 | 50 | 100 | 200 | 6.3 | 10 | 16 | 25 | 50 | 100 | 200 | 6.3 | 10 | 16 | 25 | 50 | 100 | 200 | 500 |
| | SIZE | 0101 | 0201 | | | 0402 | | | 0603 | | | | | | | 0805 | | | | | | | 1206 | | | | | | | |

| Letter | A | C | E | G | J | K | M | N | P | Q | X | Y | Z |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Max. Thickness | 0.33 (0.013) | 0.56 (0.022) | 0.71 (0.028) | 0.90 (0.035) | 0.94 (0.037) | 1.02 (0.040) | 1.27 (0.050) | 1.40 (0.055) | 1.52 (0.060) | 1.78 (0.070) | 2.29 (0.090) | 2.54 (0.100) | 2.79 (0.110) |
| | PAPER | | | | | EMBOSSED | | | | | | | |


*Optional Specifications – Contact factory

# X7R Dielectric

## Capacitance Range

### PREFERRED SIZES ARE SHADED

| SIZE | | 1210 | | | | | | | 1812 | | | | 1825 | | 2220 | | | | 2225 | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Soldering | | Reflow Only | | | | | | | Reflow Only | | | | Reflow Only | | Reflow Only | | | | Reflow Only | |
| Packaging | | Paper/Embossed | | | | | | | All Embossed | | | | All Embossed | | All Embossed | | | | All Embossed | |
| (L) Length | mm (in.) | 3.20 ± 0.20 (0.126 ± 0.008) | | | | | | | 4.50 ± 0.30 (0.177 ± 0.012) | | | | 4.50 ± 0.30 (0.177 ± 0.012) | | 5.70 ± 0.40 (0.225 ± 0.016) | | | | 5.72 ± 0.25 (0.225 ± 0.010) | |
| (W) Width | mm (in.) | 2.50 ± 0.20 (0.098 ± 0.008) | | | | | | | 3.20 ± 0.20 (0.126 ± 0.008) | | | | 6.40 ± 0.40 (0.252 ± 0.016) | | 5.00 ± 0.40 (0.197 ± 0.016) | | | | 6.35 ± 0.25 (0.250 ± 0.010) | |
| (t) Terminal | mm (in.) | 0.50 ± 0.25 (0.020 ± 0.010) | | | | | | | 0.61 ± 0.36 (0.024 ± 0.014) | | | | 0.61 ± 0.36 (0.024 ± 0.014) | | 0.64 ± 0.39 (0.025 ± 0.015) | | | | 0.64 ± 0.39 (0.025 ± 0.015) | |
| | WVDC | 10 | 16 | 25 | 50 | 100 | 200 | 500 | 50 | 100 | 200 | 500 | 50 | 100 | 25 | 50 | 100 | 200 | 50 | 100 |
| Cap (pF) | 100 | | | | | | | | | | | | | | | | | | | |
| | 150 | | | | | | | | | | | | | | | | | | | |
| | 220 | | | | | | | | | | | | | | | | | | | |
| | 330 | | | | | | | | | | | | | | | | | | | |
| | 470 | | | | | | | | | | | | | | | | | | | |
| | 680 | | | | | | | | | | | | | | | | | | | |
| | 1000 | | | | | | | | | | | | | | | | | | | |
| | 1500 | J | J | J | J | J | J | M | | | | | | | | | | | | |
| | 2200 | J | J | J | J | J | J | M | | | | | | | | | | | | |
| | 3300 | J | J | J | J | J | J | M | | | | | | | | | | | | |
| | 4700 | J | J | J | J | J | J | M | | | | | | | | | | | | |
| | 6800 | J | J | J | J | J | J | M | | | | | | | | | | | | |
| Cap (µF) | 0.010 | J | J | J | J | J | J | M | K | K | K | K | M | M | | X | X | X | M | P |
| | 0.015 | J | J | J | J | J | J | P | K | K | K | P | M | M | | X | X | X | M | P |
| | 0.022 | J | J | J | J | J | J | Q | K | K | K | P | M | M | | X | X | X | M | P |
| | 0.033 | J | J | J | J | J | J | Q | K | K | K | X | M | M | | X | X | X | M | P |
| | 0.047 | J | J | J | J | J | J | | K | K | K | Z | M | M | | X | X | X | M | P |
| | 0.068 | J | J | J | J | J | M | | K | K | K | Z | M | M | | X | X | X | M | P |
| | 0.10 | J | J | J | J | J | M | | K | K | K | Z | M | M | | X | X | X | M | P |
| | 0.15 | J | J | J | J | M | Z | | K | K | P | | M | M | | X | X | X | M | P |
| | 0.22 | J | J | J | J | P | Z | | K | K | P | | M | M | | X | X | X | M | P |
| | 0.33 | J | J | J | J | Q | | | K | M | X | | M | M | | X | X | X | M | P |
| | 0.47 | M | M | M | M | Q | | | K | P | | | M | M | | X | X | X | M | P |
| | 0.68 | M | M | P | X | X | | | M | Q | | | M | P | | X | X | | M | P |
| | 1.0 | N | N | P | X | Z | | | M | X | | | M | P | | X | X | | M | P |
| | 1.5 | N | N | Z | Z | Z | | | Z | Z | | | M | | | X | X | | M | X |
| | 2.2 | X | X | Z | Z | Z | | | Z | Z | | | | | | X | X | | M | |
| | 3.3 | X | X | Z | Z | | | | Z | | | | | | | X | Z | | | |
| | 4.7 | X | X | Z | Z | | | | Z | | | | | | | X | Z | | | |
| | 10 | Z | Z | Z* | | | | | | | | | | | | Z | | | | |
| | 22 | Z* | Z* | | | | | | | | | | | | Z | | | | | |
| | 47 | | | | | | | | | | | | | | | | | | | |
| | 100 | | | | | | | | | | | | | | | | | | | |
| | WVDC | 10 | 16 | 25 | 50 | 100 | 200 | 500 | 50 | 100 | 200 | 500 | 50 | 100 | 25 | 50 | 100 | 200 | 50 | 100 |
| SIZE | | 1210 | | | | | | | 1812 | | | | 1825 | | 2220 | | | | 2225 | |




| Letter | A | C | E | G | J | K | M | N | P | Q | X | Y | Z |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Max. Thickness | 0.33 (0.013) | 0.56 (0.022) | 0.71 (0.028) | 0.90 (0.035) | 0.94 (0.037) | 1.02 (0.040) | 1.27 (0.050) | 1.40 (0.055) | 1.52 (0.060) | 1.78 (0.070) | 2.29 (0.090) | 2.54 (0.100) | 2.79 (0.110) |
| | PAPER | | | | | EMBOSSED | | | | | | | |

*Optional Specifications – Contact factory

Стандарт Электрон Связь

Мы молодая и активно развивающаяся компания в области поставок электронных компонентов. Мы поставляем электронные компоненты отечественного и импортного производства напрямую от производителей и с крупнейших складов мира.

Благодаря сотрудничеству с мировыми поставщиками мы осуществляем комплексные и плановые поставки широчайшего спектра электронных компонентов.

Собственная эффективная логистика и склад в обеспечивает надежную поставку продукции в точно указанные сроки по всей России.

Мы осуществляем техническую поддержку нашим клиентам и предпродажную проверку качества продукции. На все поставляемые продукты мы предоставляем гарантию .

Осуществляем поставки продукции под контролем ВП МО РФ на предприятия военно-промышленного комплекса России , а также работаем в рамках 275 ФЗ с открытием отдельных счетов в уполномоченном банке. Система менеджмента качества компании соответствует требованиям ГОСТ ISO 9001.

Минимальные сроки поставки, гибкие цены, неограниченный ассортимент и индивидуальный подход к клиентам являются основой для выстраивания долгосрочного и эффективного сотрудничества с предприятиями радиоэлектронной промышленности, предприятиями ВПК и научно-исследовательскими институтами России.

С нами вы становитесь еще успешнее!

**Наши контакты:**

**Телефон:** +7 812 627 14 35

**Электронная почта:** sales@st-electron.ru

**Адрес:** 198099, Санкт-Петербург, Промышленная ул, дом № 19, литера Н, помещение 100-Н Офис 331