Innovative Service Around the Globe YAGEO

DATA SHEET

SURFACE-MOUNT CERAMIC MULTILAYER CAPACITORS

C-Array

NP0/X7R/Y5V

16 V TO 50 V

sizes 0508 (4 x 0402) / 0612 (4 x 0603)

RoHS compliant & Halogen Free

YAGEO Phycomp

Product Specification – May 22, 2014 V. 3

SCOPE

This specification describes NP0/X7R/Y5V 4-capacitor Array with lead-free terminations.

APPLICATIONS

- Professional electronics
- High density consumer electronics

FEATURES

- Supplied in tape on reel
- Nickel-barrier end termination
- 0508 (4x0402) / 0612 (4x0603) capacitors (of the same capacitance value) per array
- Less than 50% board space of an equivalent discrete component
- High volumetric efficiency
- Increased throughout, by time saved in mounting
- RoHS compliant
- Halogen Free compliant

ORDERING INFORMATION - GLOBAL PART NUMBER, PHYCOMP CTC & 12NC

All part numbers are identified by the series, size, tolerance, TC material, packing style, voltage, process code, termination and capacitance value.

Please note that 12 digits ordering code will expire at the end of 2010.

YAGEO BRAND ordering code

GLOBAL PART NUMBER (PREFERRED)

CA	XXXX	X	X	XXX	X	B	X	XXX
	(1)	(2)	(3)	(4)	(5)		(6)	(7)

(1) SIZE – INCH BASED (METRIC)

0508 (1220)

0612 (1632)

(2) TOLERANCE

J = ±5%

K = ±10%

M = ±20%

Z = -20% to +80%

(3) PACKING STYLE

R = Paper/PE taping reel; Reel 7 inch

P = Paper/PE taping reel; Reel 13 inch

(4) TC MATERIAL

NPO

X7R

Y5V

(5) RATED VOLTAGE

7 = 16 V

8 = 25 V

9 = 50 V

(6) PROCESS

N = NP0

B = class 2 material

(7) CAPACITANCE VALUE

2 significant digits+number of zeros

The 3rd digit signifies the multiplying factor, and letter R is decimal point

Example: 121 = 12×10^1 = 120 pF

CONSTRUCTION

The capacitor consists of a rectangular block of ceramic dielectric in which a number of interleaved metal electrodes are contained. This structure gives rise to a high capacitance per unit volume.

The inner electrodes are connected to the two end terminations and finally covered with a layer of plated tin (NiSn).

The terminations are lead-free. An outline of the structure is shown in Fig.1.



Fig. 1 Simplified outline

DIMENSIONS

Table 1

TYPE	0508 (4 X 0402)	0612 (4 X 0603)
L (mm)	2.0 ±0.15	3.2 ±0.15
W (mm)	1.25 ±0.15	1.60 ±0.15
$T_{min.}$ (mm)	0.50	0.70
$T_{max.}$ (mm)	0.70	0.90
A (mm)	0.28 ±0.10	0.4 ±0.10
B (mm)	0.2 ±0.10	0.3 ±0.20
P (mm)	0.5 ±0.10	0.8 ±0.10

OUTLINES

For dimensions see Table 1



Fig. 2 Surface mounted multilayer ceramic capacitor dimension

CAPACITANCE RANGE & THICKNESS FOR 4C-ARRAY

Table 2 Temperature characteristic material from NP0

CAPACITANCE	0508 (4 x 0402)	0612 (4 x 0603)	
	50 V	50 V	100V
10 pF	0.6±0.1		
15 pF			
18 pF			
22 pF			
33 pF			
39 pF			
47 pF			
56 pF			
68 pF			
82 pF		0.8±0.1	0.8±0.1
100 pF			
120 pF			
150 pF			
180 pF			
220 pF			
270 pF			
330 pF			
390 pF			
470 pF			
560 pF			
680 pF			
820 pF			
1.0 nF			

NOTE

Values in shaded cells indicate thickness class in mm

CAPACITANCE RANGE & THICKNESS FOR 4C-ARRAY

Table 3 Temperature characteristic material from X7R

CAPACITANCE	0508 (4 x 0402)			0612 (4 x 0603)		
	16 V	25 V	50 V	16 V	25 V	50 V
180 pF						
220 pF						
270 pF						
330 pF						
390 pF						
470 pF						
560 pF						
680 pF						
820 pF						
1.0 nF			0.6±0.1			
1.2 nF						0.8±0.1
1.5 nF						
1.8 nF						
2.2 nF						
2.7 nF					0.8±0.1	
3.3 nF		0.6±0.1				
3.9 nF				0.8±0.1		
4.7 nF						
5.6 nF						
6.8 nF						
8.2 nF	0.6±0.1					
10 nF						
12 nF						
15 nF						
18 nF						
22 nF						
27 nF						
33 nF						
47 nF						
56 nF						
68 nF						
82 nF						
100 nF						

NOTE

Values in shaded cells indicate thickness class in mm

CAPACITANCE RANGE & THICKNESS FOR 4C-ARRAY

Table 4 Temperature characteristic material from Y5V

CAPACITANCE	0612 (4 x 0603)
	25 V
10 nF	
22 nF	0.6±0.1
47 nF	
100 nF	

NOTE

Values in shaded cells indicate thickness class in mm

THICKNESS CLASSES AND PACKING QUANTITY

Table 5

SIZE CODE	THICKNESS CLASSIFICATION	TAPE WIDTH	QUANTITY PER REEL	Ø180 MM / 7 INCH Paper	Ø180 MM / 13 INCH Paper
0508	0.6 ±0.1 mm	8 mm		4,000	20,000
0612	0.8 ±0.1 mm	8 mm		4,000	15,000

ELECTRICAL CHARACTERISTICS

4C-ARRAY DIELECTRIC CAPACITORS; NISN TERMINATIONS

Unless otherwise stated all electrical values apply at an ambient temperature of 20±1 °C, an atmospheric pressure of 86 to 106 kPa, and a relative humidity of 63 to 67%.

Table 6

DESCRIPTION		VALUE
Capacitance range		10 pF to 100 nF
Rated voltage		
	NP0	50 V
	X7R	0508: 16 V, 0612: 16 V to 50 V
	Y5V	0612: 25 V
Capacitance tolerance		
	NP0	±5%, ±10%
	X7R	±10%, ±20%
	Y5V	–20% to +80%
Dissipation factor (D.F.)		
	NP0	≤ 0.1%
	X7R	16 V ≤ 3.5%, 25V ≤ 2.5%, 50V ≤ 2.5% 12nF~100nF, Df ≤5%
	Y5V	0508 ≤ 9%, 0612 ≤ 7%
Insulation resistance after 1 minute at U_r (DC)		R_{ins} ≥ 10 GΩ or R_{ins} × C_r ≥ 500 seconds whichever is less
Maximum capacitance change as a function of temperature (temperature characteristic/coefficient):		
	NP0	±30 ppm/°C
	X7R	±15%
	Y5V	+22% to –82%
Operating temperature range:		
	NP0	–55 °C to +125 °C
	X7R	–55 °C to +125 °C
	Y5V	–30 °C to +85 °C

NP0 0508/0612 50 V

Sample limits (broken lines)
Requirement levels (dotted lines)



Fig. 3 Typical temperature coefficient as a function of temperature



Fig. 4 Typical tan δ as a function of temperature



Fig. 5 Typical capacitance change with respect to the capacitance at 1 V as a function of DC voltage

X7R 0508 16 V



Fig. 6 Typical capacitance change with respect to the capacitance at 1 V as a function of DC voltage at 20 °C



Fig. 7 Typical tan δ as a function of temperature



Fig. 8 Typical capacitance change as a function of temperature

X7R 0612 16 V to 50 V

Curve 1 = 16 V product
Curve 2 = 25 V product
Curve 3 = 50 V product



Fig. 9 Typical capacitance change with respect to the capacitance at 1 V as a function of DC voltage at 25 °C

Curve 1 = 16 V product
Curve 2 = 25 V product
Curve 3 = 50 V product



Fig. 10 Typical tan δ as a function of temperature



Fig. 11 Typical capacitance change as a function of temperature

Y5V 0612 25 V



Fig. 12 Typical capacitance change with respect to the capacitance at 1 V as a function of DC voltage at 25 °C



Fig. 13 Typical tan δ as a function of temperature



Fig. 14 Typical capacitance change as a function of temperature

TESTS AND REQUIREMENTS

Table 7 Test procedures and requirements

TEST	TEST METHOD		PROCEDURE	REQUIREMENTS
Mounting	IEC 60384-21/22	4.3	The capacitors may be mounted on printed-circuit boards or ceramic substrates	No visible damage
Visual Inspection and Dimension Check		4.4	Any applicable method using × 10 magnification	In accordance with specification
Capacitance		4.5.1	Class 1: f = 1 MHz for C ≤ 1 nF, measuring at voltage 1 V_{rms} at 20 °C f = 1 KHz for C > 1 nF, measuring at voltage 1 V_{rms} at 20 °C Class 2: f = 1 KHz for C ≤ 10 μF, measuring at voltage 1 V_{rms} at 20 °C f = 120 Hz for C >10 μF, measuring at voltage 0.5 V_{rms} at 20 °C	Within specified tolerance
Dissipation Factor (D.F.)		4.5.2	Class 1: f = 1 MHz for C ≤ 1 nF , measuring at voltage 1 V_{rms} at 20 °C f = 1 KHz for C > 1 nF, measuring at voltage 1 V_{rms} at 20 °C Class 2: f = 1 KHz for C ≤ 10 μF, measuring at voltage 1 V_{rms} at 20 °C f = 120 Hz for C > 10 μF, measuring at voltage 0.5 V_{rms} at 20 °C	In accordance with specification
Insulation Resistance		4.5.3	At U_r (DC) for 1 minute	In accordance with specification

TEST	TEST METHOD	PROCEDURE	REQUIREMENTS
Temperature Coefficient	4.6	Capacitance shall be measured by the steps shown in the following table. The capacitance change should be measured after 5 min at each specified temperature stage. Step / Temperature(℃) a / 25±2 b / Lower temperature±3℃ c / 25±2 d / Upper Temperature±2℃ e / 25±2 (1) Class I Temperature Coefficient shall be calculated from the formula as below $\text{Temp, Coefficient} = \frac{C2 - C1}{C1 \times \Delta T} \times 10^6$ [ppm/℃] C1: Capacitance at step c C2: Capacitance at 125℃ ΔT: 100℃(=125℃-25℃) (2) Class II Capacitance Change shall be calculated from the formula as below $\Delta C = \frac{C2 - C1}{C1} \times 100\%$ C1: Capacitance at step c C2: Capacitance at step b or d	<General purpose series> Class1: Δ C/C: ±30ppm Class2: X7R: Δ C/C: ±15% Y5V: Δ C/C: 22~-82% <High Capacitance series> Class2: X7R/X5R: Δ C/C: ±15% Y5V: Δ C/C: 22~-82%
Adhesion	4.7	A force applied for 10 seconds to the line joining the terminations and in a plane parallel to the substrate	Force size ≥ 0603: 5N size = 0402: 2.5N size = 0201: 1N

TEST	TEST METHOD	PROCEDURE	REQUIREMENTS
Bond Strength of Plating on End Face	IEC 60384-21/22 4.8	Mounting in accordance with IEC 60384-22 paragraph 4.3 Conditions: bending 1 mm at a rate of 1 mm/s, radius jig 340 mm	No visible damage <General purpose series> ΔC/C Class 1: NP0: within ±1% or 0.5 pF, whichever is greater Class2: X5R/X7R/Y5V: ±10% <High Capacitance series> ΔC/C Class2: X5R/X7R/Y5V: ±10%
Resistance to Soldering Heat	4.9	Precondition: 150 +0/–10 °C for 1 hour, then keep for 24 ±1 hours at room temperature Preheating: for size ≤ 1206: 120 °C to 150 °C for 1 minute Preheating: for size >1206: 100 °C to 120 °C for 1 minute and 170 °C to 200 °C for 1 minute Solder bath temperature: 260 ±5 °C Dipping time: 10 ±0.5 seconds Recovery time: 24 ±2 hours	Dissolution of the end face plating shall not exceed 25% of the length of the edge concerned <General purpose series> ΔC/C Class 1: NP0: within ±0.5% or 0.5 pF, whichever is greater Class2: X5R/X7R: ±10% Y5V: ±20% <High Capacitance series> ΔC/C Class2: X5R/X7R: ±10% Y5V: ±20% D.F. within initial specified value R_{ins} within initial specified value
Solderability	4.10	Preheated the temperature of 80 °C to 140 °C and maintained for 30 seconds to 60 seconds. Test conditions for lead containing solder alloy Temperature: 235 ±5 °C Dipping time: 2 ±0.2 seconds Depth of immersion: 10 mm Alloy Composition: 60/40 Sn/Pb Number of immersions: 1 Test conditions for leadfree containing solder alloy Temperature: 245 ±5 °C Dipping time: 3 ±0.3 seconds Depth of immersion: 10 mm Alloy Composition: SAC305 Number of immersions: 1	The solder should cover over 95% of the critical area of each termination

TEST	TEST METHOD	PROCEDURE	REQUIREMENTS
Rapid Change of Temperature	IEC 60384-21/22 4.11	Preconditioning; 150 +0/–10 °C for 1 hour, then keep for 24 ±1 hours at room temperature 5 cycles with following detail: 30 minutes at lower category temperature 30 minutes at upper category temperature Recovery time 24 ±2 hours	No visual damage <General purpose series> ΔC/C Class 1: NP0: within ±1% or 1 pF, whichever is greater Class2: X5R/X7R: ±15% Y5V: ±20% <High Capacitance series> ΔC/C Class2: X5R/X7R: ±15% Y5V: ±20% D.F. meet initial specified value R_{ins} meet initial specified value
Damp Heat with U_r Load	4.13	1. Preconditioning, class 2 only: 150 +0/-10 °C /1 hour, then keep for 24 ±1 hour at room temp 2. Initial measure: Spec: refer initial spec C, D, IR 3. Damp heat test: 500 ±12 hours at 40 ±2 °C; 90 to 95% R.H. 1.0 U_r applied 4. Recovery: Class 1: 6 to 24 hours Class 2: 24 ±2 hours 5. Final measure: C, D, IR P.S. If the capacitance value is less than the minimum value permitted, then after the other measurements have been made the capacitor shall be precondition according to *"IEC 60384 4.1"* and then the requirement shall be met.	No visual damage after recovery <General purpose series> ΔC/C Class 1: NP0: within ±2% or 1 pF, whichever is greater Class2: X5R/X7R: ±15%; Y5V: ±30% D.F. Class 1: NP0: ≤ 2 x specified value Class2: X5R/X7R: ≤ 16V: ≤ 7% ≥ 25V: ≤ 5% Y5V: ≤ 15% R_{ins} Class 1: NP0: ≥ 2,500 MΩ or $R_{ins} \times C_r \geq 25s$ whichever is less Class2: X5R/X7R/Y5V: ≥ 500 MΩ or $R_{ins} \times C_r \geq 25s$ whichever is less <High Capacitance series> ΔC/C Class2: X5R/X7R: ±20%; Y5V: ±30% D.F. Class2: 2 x initial value max R_{ins} Class2: 500 MΩ or $R_{ins} \times C_r \geq 25s$, whichever is less

TEST	TEST METHOD	PROCEDURE	REQUIREMENTS
Endurance	IEC 60384-21/22 4.14	1. Preconditioning, class 2 only: 150 +0/-10 °C /1 hour, then keep for 24 ±1 hour at room temp 2. Initial measure: Spec: refer initial spec C, D, IR 3. Endurance test: Temperature: NP0/X7R: 125 °C X5R/Y5V: 85 °C Specified stress voltage applied for 1,000 hours: Applied 2.0 x U_r for general product. Applied 1.5 x U_r for high cap. product. High voltage series follows with below stress condition: Applied 1.3 x U_r for 500V series Applied 1.2 x U_r for 1KV, 2KV, 3KV series 4. Recovery time: 24 ±2 hours 5. Final measure: C, D, IR P.S. If the capacitance value is less than the minimum value permitted, then after the other measurements have been made the capacitor shall be precondition according to *"IEC 60384 4.1"* and then the requirement shall be met.	No visual damage <General purpose series> ΔC/C Class1: NP0: within ±2% or 1 pF, whichever is greater Class2: X5R/X7R: ±15%; Y5V: ±30% D.F. Class1: NP0: ≤ 2 x specified value Class2: X5R/X7R: ≤ 16V: ≤ 7% ≥ 25V: ≤ 5% Y5V: ≤ 15% R_{ins} Class1: NP0: ≥ 4,000 MΩ or R_{ins} x C_r ≥ 40s whichever is less Class2: X5R/X7R/Y5V: ≥ 1,000 MΩ or R_{ins} x C_r ≥ 50s whichever is less <High Capacitance series> ΔC/C Class 2: X5R/X7R: ±20%; Y5V: ±30% D.F. Class 2: 2 x initial value max R_{ins} Class 2: 1,000 MΩ or R_{ins} x C_r ≥ 50s, whichever is less
Voltage Proof	IEC 60384-1 4.6	Specified stress voltage applied for 1 minute U_r ≤ 100 V: series applied 2.5 U_r 100 V < U_r ≤ 200 V series applied (1.5 U_r + 100) 200 V < U_r ≤ 500 V series applied (1.3 U_r + 100) U_r > 500 V: 1.3 U_r I: 7.5 mA	No breakdown or flashover

REVISION HISTORY

REVISION	DATE	CHANGE NOTIFICATION	DESCRIPTION
Version 3	May 21, 2014	-	- Product range updated
Version 2	Jun. 17, 2013	-	- Product range updated
Version 1	Feb 05, 2010	-	- The statement of "Halogen Free" on the cover added
Version 0	Jun 22, 2009	-	- New datasheet for 4C-Array series with RoHS compliant - Replace from pdf files: 0508_16V to 50V_1, 0612_16V to 50V_0, C-Array_NP0_50V_0508_7, C-Array_NP0_50V_0612_7, C-Array_X7R_16V_25V_50V_0612_6, C-Array_X7R_16V_0508_5, C-Array_Y5V_25V_0508_0, C-Array_Y5V_25V_0612_5 - Define global part number - Description of "Halogen Free compliant" added - Test method and procedure updated

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

Yageo:

CA0612JRNPO9BN101 CA0612JRNPO9BN330 CA0612KRNPO9BN101 CA0612KRNPO9BN151 CA0612KRNPO9BN220 CA0612KRNPO9BN470 CA0612KRX7R7BB104 CA0612KRX7R8BB473 CA0612KRX7R9BB103 CA0612MRX7R7BB104 CA0612MRX7R9BB103 CA0508KRNPO9BN220 CA0508KRNPO9BN101 CA0508JRNPO9BN220 CA0612JRNPO9BN220 CA0612KRNPO9BN221 CA0612JRNPO9BN680 CA0612JRNPO9BN470 CA0508KRNPO9BN100 CA0508KRNPO9BN330 CA0612JRNPO9BN221 CA0612KRNPO9BN100 CA0508JRNPO9BN150 CA0508JRNPO9BN221 CA0612KRX7R7BB103 CA0612KRX7R9BB102 CA0612KRX7R8BB103 CA0612KRX7R7BB683

Стандарт Электрон Связь

Мы молодая и активно развивающаяся компания в области поставок электронных компонентов. Мы поставляем электронные компоненты отечественного и импортного производства напрямую от производителей и с крупнейших складов мира.

Благодаря сотрудничеству с мировыми поставщиками мы осуществляем комплексные и плановые поставки широчайшего спектра электронных компонентов.

Собственная эффективная логистика и склад в обеспечивает надежную поставку продукции в точно указанные сроки по всей России.

Мы осуществляем техническую поддержку нашим клиентам и предпродажную проверку качества продукции. На все поставляемые продукты мы предоставляем гарантию .

Осуществляем поставки продукции под контролем ВП МО РФ на предприятия военно-промышленного комплекса России , а также работаем в рамках 275 ФЗ с открытием отдельных счетов в уполномоченном банке. Система менеджмента качества компании соответствует требованиям ГОСТ ISO 9001.

Минимальные сроки поставки, гибкие цены, неограниченный ассортимент и индивидуальный подход к клиентам являются основой для выстраивания долгосрочного и эффективного сотрудничества с предприятиями радиоэлектронной промышленности, предприятиями ВПК и научно-исследовательскими институтами России.

С нами вы становитесь еще успешнее!

Наши контакты:

Телефон: +7 812 627 14 35

Электронная почта: sales@st-electron.ru

Адрес: 198099, Санкт-Петербург, Промышленная ул, дом № 19, литера Н, помещение 100-Н Офис 331